

CODICE PRODOTTO
A58

Tecnologie
UV HD GH



**SCATOLA DA 30
LENTI A CONTATTO**

Disponibile in stock e
private label

HYDROSI 100

ONE | MULTIFOCAL

TECHNICAL FILE

Materiale	Innofilcon A
Contenuto d'acqua	45%
Geometria	Asferica
Curva base	8.60 mm
Diametro	14.20 mm
Spessore centrale	0.093 mm (a -3.00 Dt)
Tinta Manipolazione	Leggermente azzurrata
Dk	70
Dk/t	103
Addizione	+1.00 - +2.50 (0.50 step)

CARATTERISTICHE DEL PRODOTTO

Realizzate con Tecnologia HD, per compensare le aberrazioni visive causate dall'applicazione della lente sull'occhio e offrire una visione più nitida e definita.

Elevata permeabilità all'ossigeno (Dk/t 103).

Con trattamento "Hydro Technology": una combinazione di polimeri idrofili che aumenta la lubrificazione superficiale della lente ed impedisce l'assorbimento delle proteine del film lacrimale.

La superficie ottica asferica è prodotta con tecnologie di alta precisione per favorire una migliore interazione con la superficie corneale.

Con filtro UV integrato nel materiale.

GAMMA POTERI

-12.00 Dt ~ +6.00 Dt

da -12.00 a -6.00 (0.50 step)
da -6.00 a +5.00 (0.25 step)
da +5.50 a +6.00 (0.50 step)

PRODUCT CODE
A58

Technologies
UV HD GH



**BOX WITH 30
CONTACT LENSES**

Available in stock and
private label

HYDROSI 100

ONE | MULTIFOCAL

TECHNICAL FILE

Material	Innofilcon A
Water content	45%
Geometry	Aspherical
Base curve	8.60 mm
Diameter	14.30 mm
Central thickness	0.093 mm (a -3.00 Dt)
Handling Tint	Light Blue
Dk	70
Dk/t	103
Addition	+1.00 - +2.50 (0.50 step)

PRODUCT FEATURES

Made with HD Technology to compensate for visual aberrations caused by the lens application on the eye and offer sharper, clearer vision

High oxygen permeability (Dk/t 103)

With “Hydro Technology” treatment: a combination of hydrophilic polymers that increases the surface lubrication of the lens and prevents the absorption of proteins from the tear film

The aspheric optical surface is produced with high-precision technologies to promote better interaction with the corneal surface

With UV filter integrated into the material

POWER RANGE

-12.00 Dt ~ +6.00 Dt

from -12.00 to -6.00 (0.50 step)
from -6.00 to +5.00 (0.25 step)
from +5.50 to +6.00 (0.50 step)